PARASILICO AM85-2 (T)



CHARACTERISTICS

- Neutral oxime curing, 1-component weatherseal silicone sealant (RTV-1)
- Very easy to apply
- Excellent adhesion to almost all building materials
- Permanent elasticity
- High resistance to ageing, weather conditions and UV

APPLICATIONS

- Has an adhesive strength without primer on the majority of materials used in building
 and engineering industries such as treated wood, aluminium, abs, steel, stainless
 steel, anodised steel, hard PVC, glass, etc. On absorbent surfaces such as concrete,
 bricks... a primer is recommended.
- Parasilico AM85-2 T is suitable for applications with permanent water load, provided that the use of a primer.

| TECHNICAL CHARACTERISTICS | | |
|--|--|--|
| Uncured sealant | | |
| Type of sealant | Polysiloxanes | |
| Curing system | Through moisture in the air | |
| Skin forming time (23°C and 50% R.H.) | 25 min. (AM85-2) 10 min. (AM85-2 T) | |
| Curing rate (23°C and 50% R.H.) | 2,5 - 3 mm after 24h | |
| Density: ISO 1183 | 1,34 g/ml (AM85-2) 1 g/ml (AM85-2 T) | |
| Processing temperature | +5°C - +40°C | |
| Shelf life, in original packing in dry conditions between +5°C - +25°C | 15 months | |
| Cured sealant | | |
| Shore A hardness: ISO 868 | 22 (AM85-1) 13 (AM85-1 T) | |
| Elastic recovery: ISO 7389 | >90% | |
| Deformation capability: ISO 11600 | 25% | |
| Modulus at 100% elongation: ISO 8339 | 0,38 N/mm² (AM85-2) 0,25 N/mm² (AM85-2 T) | |
| % Elongation at break: ISO 8339 | 280% (AM85-2) 310% (AM85-2 T) | |
| VOC | < 100 g/l | |
| Temperature resistance | -50°C - +150°C | |

PACKING AND COLOURS

12 cartridges of 300 ml/box - 100 boxes/pallet

Parasilico AM85-2: RAL 9003 signal white, RAL 9010 white, RAL 9011 black, RAL 7004 grey, RAL 7016 anthracite grey, RAL 7035 light grey

Parasilico AM85-2 T: Transparent, transparent grey, snow white

25 sausages of 400 ml/box - 48 boxes/pallet

Parasilico AM85-2: RAL 9010 white, RAL 9011 black, RAL 7004 grey, RAL 7016 anthracite grey

Parasilico AM85-2 T: Transparent, snow white

20 sausages of 600 ml/box - 45 boxes/pallet

Parasilico AM85-2: RAL 9010 white, RAL 9011 black, RAL 7004 grey, RAL 7016 anthracite grey

Parasilico AM85-2 T: Transparent, transparent grey, snow white

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply.



METHOD OF USE

Preparation

All surfaces should be dry, clean and free from dust or grease. When necessary, degrease with **Parasilico Cleaner**, MEK, alcohol or ethanol. If necessary, use a primer. It is recommended to carry out preliminary tests in order to determine the suitability of the product for its application.

Primers

| Porous surfaces | Silicone Primer Porous Surfaces | Transparent | Drying time (approx.) 60 min. |
|---------------------|-------------------------------------|-------------|-------------------------------|
| Non porous surfaces | Silicone Primer Non-porous Surfaces | Transparent | Drying time (approx.) 60 min. |

Application

- With a sealant gun (manual or pneumatic). The size and shape of the joint is very important. Avoid thin joints.
- Use in well-ventilated rooms. Good ventilation is important during application and curing of the product.
- Do not subject the joint to thermal, mechanical or chemical stress before curing is complete.

Joint dimensions (Maximum joint width: 30 mm)

| Joint width | Joint depth | Allowed difference |
|-------------|-------------|--------------------|
| 3-4 mm | 3-4 mm | ± 1 mm |
| 6 mm | 6 mm | ± 1 mm |
| 8 mm | 8 mm | ± 1 mm |
| 10 mm | 6-8 mm | ± 2 mm |
| 15 mm | 10 mm | ± 2 mm |
| 20 mm | 10-12 mm | ± 2 mm |
| 25 mm | 15 mm | ± 3 mm |
| 30 mm | 18 mm | ± 3 mm |

Tooling

- If desired, smooth surface before skin formation with the Perfect Joint Tooling Agent and/or the Perfect Joint Tool.
- Avoid that tooling agent ends up on the surface before applying the silicone. Silicone does not adhere to a damp surface.

Cleaning

- Before curing: Tools, surfaces and uncured residues can be removed with **Parasilico Cleaner, Multi-Purpose Super Cleaner** or **Cleaning Wipes.**
- After curing: Remove cured sealant mechanically. Remainder of silicone can be removed with Silicone Remover.

Repairing With the same product.

SAFETY Refer to the packaging or safety data sheet for additional information.

POINTS OF ATTENTION

- Not compatible with the edge seal of insulating glazing and the PVB film of safety glass. Avoid direct contact.
- White colours and transparent can yellow light in the total absence of UV light or through contact with smoke or detergents.
- Parasilico AM85-2 is not suitable for applications with permanent water load.
- For sanitary applications, Parasilico Prestige (T), Parasilico Sanitair N (T) or Parasilico Premium T is recommended.
- Use Parasilico Prestige Colour T in swimming pool applications.
- Do not use on natural stone (staining). On natural stone use Parasilico Prestige (T) or Parasilico NS (T).
- Use Paracol Miroseal for gluing mirrors.
- Use Parasilico PL on polyacrylate and polycarbonate.
- On PE, PP, PTFE (Teflon®) and bituminous substrates there is no adhesion.
- Not paintable.

TECHNICAL APPROVALS

- SNJF Société National du Joint Français
 Parasilico AM85-2 FACADE n° 4395 VTRAGE n° 4398
 Parasilico AM85-2 T FACADE n° 4401 VITRAGE n° 4404
- CE
- Meets the requirements of the standards: ISO 11600 F&G 25 LM



EN 15651-1 F EXT - INT EN 15651-2 G No. DoP (Colours) MP0020092 No. DoP (Transparent base) MP0020093 * Information sur le niveau d'émission de substances volatiles dans l'air intérieur, présentant un risque de toxicité par inhalation, sur une échelle de classe allant de A+ (très faibles émissions) à C (fortes émissions).



This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply.

