## **PARAPLAST SUPER**



## **CHARACTERISTICS**

- Single-sided, self-adhesive polyethylene strip
- Reinforced with wire
- Closed cells.
- Highly resistant to ageing
- Free of softener
- Can be combined with silicon, Thiokol or other sealants.
- Resistant to salt water, chemicals, soap and cleaning products.

## **APPLICATIONS**

Suitable for aluminium, PVC and wood frames.

TECHNICAL CHARACTERISTICS		
Density: DIN 53420	0,033 g/cm <sup>3</sup>	
Pressure resistance : DIN 53577	30% : 0,5 N/mm <sup>2</sup> 50% : 0,12 N/mm <sup>2</sup> 70% : 0,25 N/mm <sup>2</sup>	
Water absorption : DIN 53428	After 7 days : 0,7% After 28 days : 0,8%	
Water vapour permeability at thickness of 2 mm : DIN 53122	1,8 g/m² per 24 h	
Tearing resistance : DIN 53575	Length: 2,9 N/mm Transverse: 2,0 N/mm	
Elongation, expansion : DIN 53571	Length: 176% Transverse: 168%	
Temperature resistance	-80°C - +100°C	

PACKING AND MEASUREMENTS		
Measurement	Packing	Colour
9 x 2 mm	26 x 100 m/box	grey
9 x 3 mm	20 x 100 m/box	grey
9 x 4 mm	16 x 100 m/box	grey
9 x 5 mm	22 x 50 m/box	grey
15 x 3 mm	12 x 100 m/box	grey

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply.

