

**CHARACTERISTICS**

- Extremely high bonding capacity
- Double adhesive black polyethylene foam (closed cells)
- Is protected by a liner
- Resistant to water, detergents, alcohol, aliphatic solvents and some aromatic solvents

APPLICATIONS

- Bonding of divided lites.

TECHNICAL CHARACTERISTICS

Density: DIN 53420 (g/cm ³)	0.1
Adhesion 180° - 30 min. on stainless steel: FTM1	>25 N/25 mm
Adhesion: AFERA 4001	23°C: > 25 N/25 mm 70°C: > 5 N/25 mm
Cohesion test on stainless steel 1 kg - 25 mm x 25 mm: FTM 8	± 1000 hours
Cohesion: AFERA 4012	23°C: > 90 N 70°C: > 25 N
Elasticity: DIN 53455	MD 14 N/15 mm CD 10 N/15 mm
Elongation to break: DIN 53455	MD 350 % CD 350 %
Application temperature	> +10°C
Temperature resistance	-40°C - +100°C
Shelf life of unopened product	24 months
Storage conditions	Store in a dry, cool place at +15°C to +25°C.

PACKING AND COLOURS

Black
12 mm : 26 x roll 66M/box - 650 pieces/pallet
19 mm : 16 x roll 66M/box - 400 pieces/pallet
25 mm : 12 x roll 66M/box - 300 pieces/pallet
30 mm : 10 x roll 66M/box - 250 pieces/pallet

METHOD OF USE**Preparation**

- The surfaces must be solid, dry and free of dust and grease.
- If needed degrease the materials to be glued with Parasilico Cleaner, MEK, fire alcohol, ethanol.

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply