# **PARACOL MIROSEAL MS**



#### **CHARACTERISTICS**

- Adhesive
- · Permanent elasticity
- Excellent adhesion to almost all building materials
- Very high initial bonding strength ('high tack')
- Cures very rapidly at room temperature
- Solvent free

#### **APPLICATIONS**

- Bonding all types of mirrors. For fixing special kinds of mirrors a test is recommended.
- Forms a permanent water-tight and weatherproof bond to many surfaces such as glass, aluminium, etc.

TECHNICAL CHARACTERISTICS	
Type of product	MS polymer
Density (g/ml)	1.52
Temperature resistance	-40°C - +90°C
Curing system	Curing by air humidity
Curing speed at 23 degrees C and 50% R.H. (mm, after 24h)	2
Skin forming time at 23°C and 50% R.H. (min.)	25
Shore A hardness: ISO 868	50
Modulus at 100% elongation: ISO 8339 (N/mm²)	1.45
Modulus at break: ISO 8339 (N/mm²)	1.75
% Elongation at break: ISO 8339	230
Shelf life of unopened product	12 months
Storage conditions	Store in a dry, cool place at +5°C to +25°C. Keep out of direct sunlight.

# PACKING AND COLOURS 25 x cartridge 290ML/box - 1200 pieces/pallet Grey

#### **METHOD OF USE**

#### **Preparation**

- The surfaces must be solid, dry and free of dust and grease.
- If needed degrease the materials to be glued with Parasilico Cleaner, MEK, fire alcohol, ethanol.

#### **Primers**

• On highly absorbent surfaces we recommend to use the Hybrid & PU Primer (transparent or black, drying time about 15 min.).

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply



info@dl-chem.com - www.dl-chem.com

## **Application**

The adhesive must be applied in vertical stripes of max. 15 mm. There should be a gap of at least 5 mm between the mirrors and the wall. Heavy mirrors should be clamped for several hours or days.

#### Cleaning

- Clean tools with white spirit
- After curing remove mechanically.

#### **SAFETY**

Consult the safety information on the packaging and the safety data sheet for more information.

## **TECHNICAL APPROVALS**

French VOC emission class A+



This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply

