



## CHARACTERISTICS

- Construction adhesive in the form of a mastic
- Water-based
- High end strength
- With filling properties
- Very high traction adhesive: no nails or screws needed
- Low odour
- Solvent free

## APPLICATIONS

- Assembling and sealing elements in polystyrene or expanded polyurethane.
- Bonding on concrete, masonry, plaster, wood, metal, PVC, etc.

## TECHNICAL CHARACTERISTICS

Type of product	Synthetic elastomer emulsion in water
Density (g/ml)	1.65
Consistency	Pasta
Temperature resistance	-25°C - +70°C
Working time at 23 degrees C and 50% R.H.	13 - 18 minutes
VOC	< 50 g/l
Tensile strength wood/wood at 20 degrees C (kg/cm <sup>2</sup> )	45
Shelf life of unopened product	15 months
Storage conditions	Store in a dry, cool place at +5°C to +25°C. Keep out of direct sunlight.

## PACKING AND COLOURS

**25 x cartridge 310ML/box - 1200 pieces/pallet**  
White

## METHOD OF USE

### Preparation

- The surfaces must be solid, dry and free of dust and grease.
- If needed degrease the materials to be glued with Parasilico Cleaner, MEK, fire alcohol, ethanol.
- The user needs to make sure that the product is suitable for the application. Consult our technical service if necessary.

### Application

- Apply in bands or in plots on the material or substrate.
- Compress the material to be glued into the correct position.
- Repositioning is possible for 30 minutes.
- Heavy materials exceeding 8 kg/m<sup>2</sup> must be supported for 8 to 15 hours.

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply

- A good adhesion is obtained after 1 hour but wait at least 24 to 48 hours before submitting the supports to traction.

### **Cleaning**

- Before curing: Tools, surfaces and uncured residues can be removed with water.

### **SAFETY**

Consult the safety information on the packaging and the safety data sheet for more information.

### **TECHNICAL APPROVALS AND QUALITY LABELS**

- French VOC emission class A+



This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply