

# SILICONE PRIMER NON-POROUS SURFACES



## CHARACTERISTICS

- Primer for silicone sealant
- Promotes the adhesion of silicone sealant to the substrate
- Ignition point DIN 51794: +420°C

## APPLICATIONS

- Suitable for use on non porous materials, certain plastics and paints.

## TECHNICAL CHARACTERISTICS

Type of product	Silicone resin solution with a reactive addition
Density (g/ml)	0.76
Consistency	Liquid
Drying time (depending on the layer thickness and atmospheric conditions)	60 minutes
Application temperature	+5°C - +25°C
Flash point (CC, degrees C)	+9 (DIN 51755)
Self-ignition temperature	DIN 51794: +420°C
Shelf life of unopened product	12 months
Storage conditions	Store in a dry, cool place at +5°C to +25°C. Keep out of direct sunlight.

## PACKING AND COLOURS

**26 x can 250ML/box - 1664 pieces/pallet**

Transparent

**can 1l - 104 pieces/pallet**

Transparent

## METHOD OF USE

### Preparation

- The surfaces must be solid, dry and free of dust and grease.
- If needed degrease the materials to be glued with Parasilico Cleaner, MEK, fire alcohol, ethanol.

### Application

- Apply the primer to the surface with a paint brush.
- When the primer is dry, apply the silicone sealant. The faster after drying, the better. Apply the silicone sealant within 16 hours at the latest. If this time period has been exceeded, a new layer of primer must be applied.

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply

## SAFETY

Consult the safety information on the packaging and the safety data sheet for more information.

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply