

**CHARACTERISTICS**

- Flexible butyl and polyisobutylene based cordon sealant
- With protection foil
- Available in round profiles
- Resistance to water and salt water is excellent
- Resistance to detergents is very good
- Resistance to diluted acids is good
- Resistance to diluted alkalines is very good
- Resistance to alcohol is medium
- Resistance to organic solvents is bad

APPLICATIONS

- Is used for temporarily and permanent jointing in building and manufacturing industry
- For connections between ceiling plates, waterproof connections between corrugated sheets, etc.

TECHNICAL CHARACTERISTICS

| | |
|--------------------------------|---|
| Type of product | Butyl, polyisobutylene |
| Density (g/ml) | 1.85 |
| Application temperature | > +5°C |
| Temperature resistance | -50°C - +80°C |
| Plasticity | 35 120 |
| Shelf life of unopened product | 24 months |
| Storage conditions | Store in a dry, cool place at +5°C to +25°C. Keep out of direct sunlight. |

PACKING AND COLOURS

| |
|---|
| Grey |
| 6 mm : 22 x roll 8M/box - 660 pieces/pallet |
| 9,5 mm : 16 x roll 6M/box - 480 pieces/pallet |
| 13 mm : 16 x roll 4M/box - 480 pieces/pallet |

METHOD OF USE**Preparation**

- The surfaces must be solid, dry and free of dust and grease.
- If needed degrease the materials to be glued with Parasilico Cleaner, MEK, fire alcohol, ethanol.
- The user needs to make sure that the product is suitable for the application. Consult our technical service if necessary.

Application

- Cut Paraform 20 at desired length. Apply the protection foil and the band on the surfaces. Press firmly from the inside towards the outside to avoid air bubbles.

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply

- Remove the protection foil and press the parts firmly together. The parts stick immediately. After one hour the adhesion strength is optimal

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply