

**CHARACTERISTICS**

- Plastic permanent joint sealant based on linseed and soybean oil. Forms a protective plastic skin, hardens very slowly to the core.
- Instant adhesion on all clean and dry surfaces
- Paintable with most water and solvent based paints
- Reinforced by fibers
- No staining on porous materials
- Plastic permanent joint sealant
-

APPLICATIONS

- Sealing joints between windows, walls, doors, window-ledges, panels...
- Glazing joints for single glazing in, for example, greenhouses.
- Repairing old mastic joints.
- Particularly suitable for sealing removable elements.
- Only suitable for joints with low movement.

TECHNICAL CHARACTERISTICS

Type of product	Polybutene
Density (g/ml)	1.8
Application temperature	+5°C - +35°C
Temperature resistance	-20°C - +80°C
Curing system	Oxidative drying
Skin forming time at 23°C and 50% R.H. (min.)	1,440
Shelf life of unopened product	15 months
Storage conditions	Store in a dry, cool place at +5°C to +25°C. Keep out of direct sunlight.

PACKING AND COLOURS

25 x cartridge 310ML/box - 1200 pieces/pallet

Cream white, Grey

METHOD OF USE**Preparation**

- The surfaces must be solid, dry and free of dust and grease.
- If needed degrease the materials to be glued with Parasilico Cleaner, MEK, fire alcohol, ethanol.
- Use in well-ventilated rooms. Good ventilation is important during application and curing of the product.
- The user needs to make sure that the product is suitable for the application. Consult our technical service if necessary.

Application

- Apply the product from the cartridge or foil packaging with a manual or pneumatic caulking gun.
- The size and shape of the joint is very important. Avoid thin joints.

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply

Joint dimensions

- The maximum joint size is 10 x 10 mm.

Tooling

- If desired, smooth surface before skin formation with the Perfect Joint Tooling Agent and/or the Perfect Joint Tool.

Cleaning

- Clean tools with white spirit.

Paintable

- Paintable after curing with most water and solvent based paints. Curing time depends on the joint dimensions.
- Given the wide variety of paint types available, it is recommended that you test the compatibility of the sealant/adhesive with the paint in advance.
- Repainting too soon can crack the paint and/or impair the matte finish. Cracks may also appear in the paint because the paint is less flexible than the sealant.

SAFETY

Consult the safety information on the packaging and the safety data sheet for more information.

POINTS OF ATTENTION

- Not suitable for permanent submersion.
- Not suitable for use on butiminous surfaces.
- Not suitable for use on PE, PP, PA, PTFE (Teflon).
- Not suitable for expansion joints.
- Not suitable for sealing laminated glass and double glazing.

TECHNICAL APPROVALS

- French VOC emission class A+



This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply