



CHARACTERISTICS

- Liquid adhesive
- Extremely high bonding capacity
- With high quality resins and a mixture of special solvents

APPLICATIONS

- Bonding stratified or laminated panels, rubber or plastic sectionals, leather, wood, veneer, agglomerates, plywood, cork, fibro-cement, metals on themselves or in combination.
- Ideal for horizontal applications.
- Suitable for indoor use only.

TECHNICAL CHARACTERISTICS

Type of product	Polychloroprene including resins of high quality and a special mixture of aromatic-free solvents
Density (g/ml)	0.9
Application temperature	> +10°C
Temperature resistance	-40°C - +70°C
Shelf life of unopened product	18 months
Storage conditions	Store in a dry, cool place at +5°C to +25°C. Keep out of direct sunlight.

PACKING AND COLOURS

2 x can 5L/box - 216 pieces/pallet

Brown beige

12 x can 750ML/box - 600 pieces/pallet

Brown beige

METHOD OF USE

Preparation

- The surfaces must be solid, dry and free of dust and grease.
- If needed degrease the materials to be glued with Parasilico Cleaner, MEK, fire alcohol, ethanol.
- The user needs to make sure that the product is suitable for the application. Consult our technical service if necessary.

Application

- Stir the glue before using (opening time max. 45 minutes), and then apply it with a brush or a spatula.
- Let dry for 15 to 30 minutes, this time spread cannot be more precise as it depends on materials, temperature, and hygrometry.
- The elements to be glued can be pressed together as soon as the glue does not stick to the fingers anymore.
- A strong pressure should be applied to the whole surface.

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply

- After the pressing it is no longer possible to correct
- Final adherence is achieved after 48 hours

Cleaning

- Uncured, redundant product can be removed with acetone.

SAFETY

Consult the safety information on the packaging and the safety data sheet for more information.

POINTS OF ATTENTION

- Not suitable for use on PE, PP, PA, PTFE (Teflon).
- Not appropriate for use on polystyrene (XPS, EPS).
- Not suitable for use on soft PVC.

TECHNICAL APPROVALS AND QUALITY LABELS

- French VOC emission class A+



This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply