



## CHARACTERISTICS

- Extremely high bonding capacity
- With high quality resins and a mixture of special solvents
- Designed for vertical gluing
- Easy to use without draining

## APPLICATIONS

- Bonding stratified or laminated panels, rubber or plastic sectionals, leather, wood, veneer, agglomerates, plywood, cork, fibro-cement, metals on themselves or in combination.
- Ideal for vertical applications.
- Suitable for indoor use only.

## TECHNICAL CHARACTERISTICS

Type of product	Polychloroprene including resins of high quality and a special mixture of aromatic-free solvents
Density (g/ml)	0.88
Consistency	Gel
Application temperature	> +10°C
Temperature resistance	-40°C - +70°C
Shelf life of unopened product	18 months
Storage conditions	Store in a dry, cool place at +15°C to +25°C.

## PACKING AND COLOURS

**12 x can 750ML/box - 600 pieces/pallet**

Brown

**2 x bucket 5L/box - 216 pieces/pallet**

Brown

## METHOD OF USE

### Preparation

- The surfaces must be solid, dry and free of dust and grease.
- If needed degrease the materials to be glued with Parasilico Cleaner, MEK, fire alcohol, ethanol.
- The user needs to make sure that the product is suitable for the application. Consult our technical service if necessary.

### Application

- Spread the glue with a brush or a spatula.
- Spread a smooth layer of glue (150 g) on the two surfaces to be bonded.
- Let solvents escape (7 to 15 min. according to temperature and surfaces).
- The elements to be glued can be pressed together as soon as the glue does not stick to the fingers anymore.

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply

- Press the two parts together very precisely as the setting power is immediate and irreversible. After the pressing it is no longer possible to correct
- Maximum adherence is achieved after 48 to 72 hours.

### Consumption

200 - 350 g/m<sup>2</sup>

### Cleaning

- Uncured, redundant product can be removed with acetone.

## SAFETY

Consult the safety information on the packaging and the safety data sheet for more information.

## POINTS OF ATTENTION

- Not appropriate for use on polystyrene (XPS, EPS).
- Not suitable for use on soft PVC.

## TECHNICAL APPROVALS AND QUALITY LABELS

- French VOC emission class A+



This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply