



CHARACTERISTICS

- All-season foam, can be used at low temperatures.
- Good thermal and acoustic insulation
- Cured foam can be cut, sawn, plastered and painted and is resistant against water
- Construction foam with low expansion pressure (avoids material deformation)
- Precise dosing with gun

APPLICATIONS

- Sealing, insulating, and filling joints such as: wall-ceiling connections, openings in roof structures, between prefabricated elements, sealing window and door frames, skylights, chimney ledges, spaces around pipes and conduits...
- For bonding insulation boards, drywall boards, window sills, roof tiles,...
- Good adhesion to concrete, masonry, stone, wood, iron, aluminum, polystyrene, polyester, hard PVC, XPS, EPS, PUR/PIR, etc.

TECHNICAL CHARACTERISTICS

Type of product	Polyurethane-prepolymer
Application temperature	-5°C - +30°C (optimal at 20°C). Bonding of external wall insulation system (ETICS)= >+5°C
Temperature resistance	-50°C - +90°C
Curing system	Reaction by humidity
Temperature product when applying	+5°C - +25°C (ideal at 20°C)
Foam yield: TM 1003 (l)	± 53 l (750 ml bus)
Tack-free: TM 1014 (min.)	8 - 12 min.
Cutable: TM 1005 (min.)	< 30 min.
Cured in the joint 3x5cm (hour)	< 8 uur / < 24 uur
Acoustic damping index Rw: EN ISO 10140 (dB)	62
Shear strength TM 1012, moistened surface (N/cm ²)	> 45 kPa
Fire class: DIN4102-1	B3
Shelf life of unopened product	18 months

PACKING AND COLOURS

12 x can 750ML/box - 672 pieces/pallet

METHOD OF USE

Preparation

- Wear gloves and safety glasses.
- Use in well-ventilated rooms. Good ventilation is important during application and curing of the product.
- Chilled cans must be warmed up in lukewarm water. The can must not be heated above +30°C. Cans which are too hot must be cooled in water. Shake the can occasionally during this process to obtain the required temperature faster.
- The surfaces must be free of dust and grease. Always pre-moisten surfaces, because foam expands due to humidity.

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply

- Shake the can vigorously at least 20 times before use. Do not shake a can already screwed onto a gun by holding only the gun.
- Keep the can in upright position when screwing onto the NBS gun. Move the gun to the can by holding the gun handle with one hand and screwing the can with the other hand. Do not turn the can during screwing.

Application

- Hold the can upside down when extruding the foam. Dose the volume with the adaptor or by using the gun trigger and the adjustment screw.
- Fill the joints to 60-70%.
- Keep the foam can with gun or adaptor upright after use.

Cleaning

- Fresh foam spills must be removed immediately within the tack-free time with PU Foam & Gun Cleaner. Cured foam can be removed mechanically or with Parafoam Remover.

SAFETY

Consult the safety information on the packaging and the safety data sheet for more information.

POINTS OF ATTENTION

- Not suitable for use on PE, PP, PA, PTFE (Teflon).
- Do not expose to UV exposure for long periods. In case of prolonged exposure, cover the product.
- The specified technical values are obtained at +23 °C and 50% relative humidity, unless otherwise indicated. These values may vary depending on environmental factors such as temperature, humidity, and type of substrate.

TECHNICAL APPROVALS AND QUALITY LABELS

- French VOC emission class A+



This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply