

**CHARACTERISTICS**

- High quality neutral alkoxy curing, 1-component silicone sealant
- Permanent elasticity
- Very easy to apply
- High resistance to high and low temperatures
- Excellent adhesion to almost all building materials
- High resistance to UV
- Excellent flexibility
- Low elasticity modulus
- Very easy to pump and to apply, also at lower temperatures
- High resistance to ageing and weather conditions
- Excellent adhesion to lead and excellent colour match to lead
- Low odour

APPLICATIONS

- Ideal for pointing lead sheet and lead flashing into brickwork, stone and concrete.
- Sealing of joints on roofs, gutters, downpipes, parapets....

TECHNICAL CHARACTERISTICS

Type of product	Polysiloxanes
Density (g/ml)	1.21
Application temperature	+5°C - +40°C
Temperature resistance	-50°C - +150°C
Curing system	Curing by air humidity
Curing speed at 23 degrees C and 50% R.H. (mm, after 24h)	3
Skin forming time at 23°C and 50% R.H. (min.)	15
Shore A hardness: ISO 868	23
Elastic recovery capacity: ISO 7389	>80%
Maximum permissible deformation: ISO 11600	25%
Modulus at 100% elongation: ISO 8339 (N/mm ²)	0.33
% Elongation at break: ISO 8339	300
Shelf life of unopened product	12 months
Storage conditions	Store in a dry, cool place at +5°C to +25°C. Keep out of direct sunlight.

PACKING AND COLOURS

12 x cartridge 300ML/box - 1200 pieces/pallet
RAL7037 Dust grey

METHOD OF USE**Preparation**

- The surfaces must be solid, dry and free of dust and grease.
- If needed degrease the materials to be glued with Parasilico Cleaner, MEK, fire alcohol, ethanol.

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply

- Use in well-ventilated rooms. Good ventilation is important during application and curing of the product.
- It is recommended to carry out tests on every surface before use.
- The user needs to make sure that the product is suitable for the application. Consult our technical service if necessary.

Primers

- Absorbent surfaces: Silicone Primer Porous Surfaces (transparent, drying time about 60 min.).
- Non-absorbent surfaces: Silicone Primer Non-Porous Surfaces (transparent, drying time about 60 min.).
- The use of a primer may be necessary on very porous substrates, in the event of difficulty in adhesion or in demanding conditions of use.

Application

- Apply the product from the cartridge or foil packaging with a manual or pneumatic caulking gun.
- The size and shape of the joint is very important. Avoid thin joints.
- Do not subject the joint to thermal, mechanical or chemical stress before curing is complete.

Joint dimensions

- Suitable joint widths from 5 mm to 30 mm
- Joints with a width up to 10 mm: joint depth should equal joint width. Joints wider than 10 mm: joint depth = (joint width/3) + 6 mm.

Tooling

- If desired, smooth surface before skin formation with the Perfect Joint Tooling Agent and/or the Perfect Joint Tool
- Avoid that tooling agent ends up on the surface before applying the silicone. Silicone does not adhere to a damp surface.

Cleaning

- Tools, surfaces and uncured residues can be removed with Parasilico Cleaner, Multi-Purpose Super Cleaner or Cleaning Wipes. Remainder of silicone can be removed with Silicone Remover after curing.

Repairing

It is recommended to use the same product.

SAFETY

Consult the safety information on the packaging and the safety data sheet for more information.

POINTS OF ATTENTION

- Not suitable for permanent submersion.
- Not suitable for use on butiminous surfaces.
- Not suitable for use on PE, PP, PA, PTFE (Teflon).
- Not suitable for use on natural stone (can cause stains).
- Not paintable.

TECHNICAL APPROVALS

- French VOC emission class A+

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply



This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply