



## CHARACTERISTICS

- Does not react to components of the cured concrete (with other types of silicone the edges of the concrete blocks might look crumbled after the curing of the concrete). The cured silicone can be easily removed from concrete.
- Only 1 coat needed
- Quickly continue working
- Bituminous primer
- Adheres to concrete, brick, metal and bituminous substrates

## APPLICATIONS

- Fixing dusty and absorbent surfaces.
- As a bonding layer for applying roofing or bituminous renovation products.

## TECHNICAL CHARACTERISTICS

Type of product	Bitumen and solvents
Density (g/ml)	0.89
Consistency	Liquid
Viscosity	9 - 14 mm <sup>2</sup> /sec (Ubbelohde 40°C)
Drying time (depending on the layer thickness and atmospheric conditions)	30 minutes
Application temperature	+5°C - +30°C
Dry matter content	±46%
Shelf life of unopened product	36 months
Storage conditions	Transport and store upright in a dry, cool place at +5°C to +25°C.

## PACKING AND COLOURS

**2 x can 5L/box - 120 pieces/pallet**  
Black

## METHOD OF USE

### Preparation

- The surfaces must be solid, dry and free of dust and grease.
- Stir the product well.
- Remove green algae with a stiff brush.

### Application

- Apply in one thin layer.
- Allow to dry out completely before continuing work.
- Apply with a brush or roller.

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply

## Consumption

Bitumen: 5 m<sup>2</sup>/l, Concrete: 3-4 m<sup>2</sup>/l, Metal and fiber cement: 10 m<sup>2</sup>/l

## Cleaning

- Clean tools with white spirit.

## SAFETY

Consult the safety information on the packaging and the safety data sheet for more information.

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply