PARAROOF RENOVATION



CHARACTERISTICS

- High resistance to UV
- · Semi-liquid bituminous roof coating
- High resistance to ageing and weather conditions
- Reinforced by fibers
- Extends lifespan
- · High resistance to atmospheric load

APPLICATIONS

 Repair, nourish and maintain existing bituminous roofing materials, fibre cement boards and concrete

TECHNICAL CHARACTERISTICS	
Type of product	Bitumen with fibre reinforcement, additives and solvents
Density (g/ml)	1.02
Consistency	Liquid pasta
Viscosity	7.500 - 11.500 mPa.s (Haake 25°C)
Drying time (depending on the layer thickness and atmospheric conditions)	24 hours
Application temperature	-5°C - +35°C
Dry matter content	±70%
Shelf life of unopened product	36 months
Storage conditions	Transport and store upright in a dry, cool place at +5°C to +25°C.

PACKING AND COLOURS
barrel 25I - 22 pieces/pallet Black
can 5I - 120 pieces/pallet Black

METHOD OF USE

Preparation

- The surfaces must be solid, dry and free of dust and grease.
- Degrease and remove rust from corroded metal parts. Should the roof be in a poor condition or already display leaks, first make waterproof with Pararoof Renovation.
- Stir the product well.
- Remove green algae with a stiff brush.
- Address aging signs of the roof: open blisters and seal with Pararoof Cold Glue. Seal cracks with Pararoof Bitumen or Pararoof Super.

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply



Last Update: 30-04-2024

Primers

• On a very absorbent or very dusty surface (concrete, cement, etc.) first apply a coat of Pararoof Quick Primer (drying time 30 min).

Application

- Apply in 2 coats for maximum protection. Apply the second coat only after complete drying of the first coat (after ±24 hours, depending on temperature and weather conditions).
- Apply with a brush or roller.

Consumption

0.4 l/m² per layer

Cleaning

· Clean tools with white spirit.

SAFETY

Consult the safety information on the packaging and the safety data sheet for more information.

POINTS OF ATTENTION

- Do not apply on surfaces that are too hot.
- The applied layers must not get wet during drying to prevent cracking.
- Do not use for roofs subject to foot traffic.
- Apply the second coat only after complete curing of the first coat.
- For optimal and long-lasting protection against aging effects under the influence of sunlight, a finishing layer based on Pararoof Reflex can be applied after complete curing of the renovation layer.

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply



Last Update: 30-04-2024

info@dl-chem.com - www.dl-chem.com