



## CHARACTERISTICS

- High resistance to UV
- Semi-liquid bituminous roof coating
- High resistance to ageing and weather conditions
- Reinforced by fibers
- Extends lifespan
- High resistance to atmospheric load

## APPLICATIONS

- Repair, nourish and maintain existing bituminous roofing materials, fibre cement boards and concrete

## TECHNICAL CHARACTERISTICS

Type of product	Bitumen with fibre reinforcement, additives and solvents
Density (g/ml)	1.02
Consistency	Liquid pasta
Viscosity	7.500 - 11.500 mPa.s (Haake 25°C)
Drying time (depending on the layer thickness and atmospheric conditions)	24 hours
Application temperature	-5°C - +35°C
Dry matter content	±70%
Shelf life of unopened product	36 months
Storage conditions	Transport and store upright in a dry, cool place at +5°C to +25°C.

## PACKING AND COLOURS

<b>barrel 25l - 22 pieces/pallet</b> Black
<b>can 5l - 120 pieces/pallet</b> Black

## METHOD OF USE

### Preparation

- The surfaces must be solid, dry and free of dust and grease.
- Degrease and remove rust from corroded metal parts. Should the roof be in a poor condition or already display leaks, first make waterproof with Pararroof Renovation.
- Stir the product well.
- Remove green algae with a stiff brush.
- Address aging signs of the roof: open blisters and seal with Pararroof Cold Glue. Seal cracks with Pararroof Bitumen or Pararroof Super.

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply

## Primers

- On a very absorbent or very dusty surface (concrete, cement, etc.) first apply a coat of Pararoom Quick Primer (drying time 30 min).

## Application

- Apply in 2 coats for maximum protection. Apply the second coat only after complete drying of the first coat (after  $\pm 24$  hours, depending on temperature and weather conditions).
- Apply with a brush or roller.

## Consumption

0.4 l/m<sup>2</sup> per layer

## Cleaning

- Clean tools with white spirit.

## SAFETY

Consult the safety information on the packaging and the safety data sheet for more information.

## POINTS OF ATTENTION

- Do not apply on surfaces that are too hot.
- The applied layers must not get wet during drying to prevent cracking.
- Do not use for roofs subject to foot traffic.
- Apply the second coat only after complete curing of the first coat.
- For optimal and long-lasting protection against aging effects under the influence of sunlight, a finishing layer based on Pararoom Reflex can be applied after complete curing of the renovation layer.

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply