

**CHARACTERISTICS**

- One component glue
- In special roofing tile colour
- Complies with standard NF P 85-611: bonding of Roman-style hollow roof tiles

APPLICATIONS

- Sealing of connection joints in building and construction.
- Bond hollow roof tiles together, on wooden battens, and cement fiberboards. No need to nail or mortar the hollow roof tiles.

TECHNICAL CHARACTERISTICS

Type of product	Elastomers
Density (g/ml)	1.35
Application temperature	+5°C - +40°C
Temperature resistance	-50°C - +100°C
Curing system	Curing by air humidity
Curing speed at 23 degrees C and 50% R.H. (mm, after 24h)	3
Skin forming time at 23°C and 50% R.H. (min.)	25
Shore A hardness: ISO 868	20
Elastic recovery capacity: ISO 7389	> 90
Modulus at 100% elongation: ISO 8339 (N/mm ²)	0.36
% Elongation at break: ISO 8339	260
Shelf life of unopened product	12 months
Storage conditions	Store in a dry, cool place at +5°C to +25°C. Keep out of direct sunlight.

PACKING AND COLOURS

12 x cartridge 300ML/box - 1200 pieces/pallet
Terracotta

METHOD OF USE**Preparation**

- The surfaces must be solid, dry and free of dust and grease.
- If needed degrease the materials to be glued with Parasilico Cleaner, MEK, fire alcohol, ethanol.
- It is recommended to carry out tests on every surface before use.
- The user needs to make sure that the product is suitable for the application. Consult our technical service if necessary.

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply

Primers

- Absorbent surfaces: Silicone Primer Porous Surfaces (transparent, drying time about 60 min.).

Application

- Apply the product from the cartridge or foil packaging with a manual or pneumatic caulking gun.

Cleaning

- Tools, surfaces and uncured residues can be removed with Parasilico Cleaner, Multi-Purpose Super Cleaner or Cleaning Wipes. Remainder of silicone can be removed with Silicone Remover after curing.

Repairing

It is recommended to use the same product.

SAFETY

Consult the safety information on the packaging and the safety data sheet for more information.

TECHNICAL APPROVALS

- CEBTP : Rapport n° B252.3.078/1 : essais selon NF P 85-611 mastics pour collage de tuiles canal.



This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply