



CHARACTERISTICS

- Repair sealant
- Ready-to-use
- Grainy structure
- Paintable after curing
- Solvent and phthalate free

APPLICATIONS

- Repairing joints between bricks and façade masonry.
- Filling of fissures and cracks.
- Suitable for all porous surfaces (wood, stone, concrete, plaster...), metal and ceramic tiles.

TECHNICAL CHARACTERISTICS

| | |
|---|---|
| Type of product | Acrylates |
| Density (g/ml) | 1.76 |
| Consistency | Pasta |
| Application temperature | +5°C - +40°C |
| Temperature resistance | -20°C - +80°C |
| Curing system | Evaporation of water |
| Curing speed at 23 degrees C and 50% R.H. (mm, after 24h) | 0.5 |
| Skin forming time at 23°C and 50% R.H. (min.) | 30 |
| Shore A hardness: ISO 868 | 65 |
| Shelf life of unopened product | 15 months |
| Storage conditions | Store in a dry, cool place at +5°C to +25°C. Keep out of direct sunlight. |

PACKING AND COLOURS

12 x cartridge 300ML/box - 1200 pieces/pallet

Cement grey, Ton pierre

METHOD OF USE

Preparation

- Use in well-ventilated rooms. Good ventilation is important during application and curing of the product.
- The surfaces must be solid, dry and free of dust and grease.
- If needed degrease the materials to be glued with Parasilico Cleaner, MEK, fire alcohol, ethanol.
- The user needs to make sure that the product is suitable for the application. Consult our technical service if necessary.

Application

- Apply the product from the cartridge or foil packaging with a manual or pneumatic caulking gun.

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply

- The size and shape of the joint is very important. Avoid thin joints.
- Do not subject the joint to thermal, mechanical or chemical stress before curing is complete.

Tooling

- Smooth surface before skin formation with Perfect Joint Tooling Agent and/or the Perfect Joint Tool.

Cleaning

- Before curing: Tools, surfaces and uncured residues can be removed with water.

Repairing

It is recommended to use the same product.

SAFETY

Consult the safety information on the packaging and the safety data sheet for more information.

POINTS OF ATTENTION

- Not suitable for permanent submersion.
- Do not apply in the case of risk of rain and frost.
- Not suitable for sealing joints around windows and doors.

TECHNICAL APPROVALS AND QUALITY LABELS

- French VOC emission class A+



This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply