PARAHEAT



CHARACTERISTICS

- Ready-to-use
- Paintable after curing
- Heat resistant to 1250°C

APPLICATIONS

- Permanently repairing and sealing joints, cracks and fissures around fireplaces, fire stoves, chimneys and ovens.
- Good adhesion to metal, brick and concrete surfaces. No primer needed.
- Suitable for indoor use only.
- Has an adhesive strength without primer on the majority of materials used in building and engineering industries such as treated wood, aluminium, abs, steel, stainless steel, anodised steel, hard PVC, glass, etc

TECHNICAL CHARACTERISTICS	
Density (g/ml)	1.9
Consistency	Pasta
Application temperature	+5°C - +40°C
Temperature resistance	up to 1250°C
рН	10
Shrinkage: ISO 10563	< 15%
Skin forming time at 23°C and 50% R.H. (min.)	30
Shore A hardness: ISO 868	90
Maximum permissible deformation: ISO 11600	3%
Shelf life of unopened product	9mnd
Storage conditions	Store in a dry, cool place at $+5^{\circ}$ C to $+25^{\circ}$ C. Keep out of direct sunlight.

PACKING AND COLOURS

25 x cartridge 310ML/box - 1200 pieces/pallet Anthracite grey

METHOD OF USE

Preparation

- Use in well-ventilated rooms. Good ventilation is important during application and curing of the product.
- The surfaces must be solid, dry and free of dust and grease.
- If needed degrease the materials to be glued with Parasilico Cleaner, MEK, fire alcohol, ethanol.
- The user needs to make sure that the product is suitable for the application. Consult our technical service if necessary.

Application

- Apply the product from the cartridge or foil packaging with a manual or pneumatic caulking gun.
- The size and shape of the joint is very important. Avoid thin joints.

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply



• Do not subject the joint to thermal, mechanical or chemical stress before curing is complete.

Tooling

• Smooth surface before skin formation with Perfect Joint Tooling Agent and/or the Perfect Joint Tool.

Cleaning

- Before curing: Tools, surfaces and uncured residues can be removed with water
- After curing remove mechanically.

SAFETY

Consult the safety information on the packaging and the safety data sheet for more information.

POINTS OF ATTENTION

- Not suitable for application outside.
- Not recommend for use in central heating systems or gas pipes. Application to electrical devices can be dangerous (in connection with the conductivity of the product).

TECHNICAL APPROVALS AND QUALITY LABELS

French VOC emission class A+



This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply

